

## Conergy PM 225P-245P

The Conergy PM 225P–245P solar modules offer a high level of module output at an attractive price/performance ratio. The modules are equipped with 60 efficient, polycrystalline cells, come with a positive only power tolerance, and are characterized by high yields and a long service life. As with all Conergy modules, the Conergy PM is built to our exacting quality assurance and control standards. Thanks to their performance, high quality of manufacture, value, and familiar form factor, the Conergy PM is perfect for nearly any application.



## Benefits for the system operator

- | Attractive price/performance ratio
- | High module output
- Certification in accordance with UL1703 (USA and Canada), IEC/EN 61215 Ed. 2 and IEC/EN 61730
- | Positive performance tolerance of +3 %
- Secure investment decision thanks to a 10-year product warranty

## Benefits for the installer

- Simple installation thanks to industry standard connectors and mounting methods
- Reliable, low maintenance modules resulting from Conergy's exceptional quality control program



## Conergy PM 225P-245P



Grounding hole

40 mm/1.57 in

40 mm/1.57 in

40 mm/1.57 in

1,000 mm/39.37 in

Terminal box

417 mm/

427 mm/

427 mm/

427 mm/

427 mm/

437 mm/

440 mm/1.57 in

440 mm/1.57 in

1,000 mm/32.83 in

Module dimensions  $(L \times W \times H)^1$ 

Cell dimensions: Number of cells:

Cell type: NOCT:<sup>2</sup>

Maximum permissible load:3

Front cover type:
Cable:
Plug type:
Module weight:4

Module weight:<sup>4</sup> 20 kg/44 lbs Certification: In accordance

iffication: In accordance with UL1703 (USA and Canada), IEC/EN 61215 Ed. 2 and IEC/EN 61730, ISO 9001:2008, ISO 14001:2004

Polycrystalline

5,400 Pa/113 psf Patterned solar glass

4mm<sup>2</sup>/12AWG, PV Wire

MC4 or MC4-compatible

46° C±2° C

Product warranty: 5

Materials and workmanship

Performance 1<sup>5</sup>
Performance 2<sup>5</sup>
Maximum permissible
system voltage:

Maximum series fuse rating:

Frame material:

10 years

10 years, 90% of nominal output 25 years, 80% of nominal output

1,668 x 1,000 x 40 mm/65.67 x 39.37 x 1.57 in

156 x 156 mm/6.14 x 6.14 in

600V/1,000 V UL/IEC

15 A

Anodised aluminum

Conergy PM	225P	230P	235P	240P	245P
Electrical ratings under standard test conditions <sup>6</sup>					
Nominal output (P <sub>nom</sub> )	225 W	230 W	235 W	240 W	245 W
Performance tolerance	-0/+3 %	-0/+3 %	-0/+3 %	-0/+3 %	-0/+3 %
Module efficiency (P <sub>nom</sub> )	13.71 %	13.80 %	14.10 %	14.39 %	14.69%
MPP voltage ( $V_{mpp}$ ) $^7$	28.91 V	29.23V	29.44V	29.65 V	29.87 V
MPP current (I <sub>mpp</sub> ) <sup>7</sup>	7.91 A	7.94 A	8.02A	8.10 A	8.18 A
Open-circuit voltage ( $V_{oc}$ ) $^7$	36.79 V	37.01 V	37.21 V	37.42 V	37.63 V
Short-circuit current (I <sub>sc</sub> ) <sup>7</sup>	8.46 A	8.49A	8.55 A	8.62A	8.68 A
Temperature coefficient ( $P_{mpp}$ )	−0.44 %/° C				
Temperature coefficient ( $V_{\text{oc}}$ ), absolute	−0.118 V/° C	-0.118 V/° C	−0.119 V/° C	−0.120 V/° C	−0.120 V/° C
Temperature coefficient ( $V_{\text{oc}}$ ), in per cent	−0.32 %/° C				
Temperature coefficient ( $I_{sc}$ ), absolute	3.38 mA/° C	3.40 mA/° C	3.42 mA/° C	3.45 mA/° C	3.47 mA/° C
Temperature coefficient ( $I_{sc}$ ), in per cent	0.04 %/° C				
Electrical rating at 800 W/m², NOCT and AM 1.5					
Power (P <sub>mpp</sub> )	168.9 Wp	171.5 Wp	174.5 Wp	177.5 Wp	180.6 Wp
Open-circuit voltage ( $V_{oc}$ )	33.82V	34.03V	34.21 V	34.41 V	34.60 V
Short-circuit current (I <sub>sc</sub> )	6.82A	6.85A	6.90A	6.95A	7.00 A
Voltage (V <sub>mpp</sub> )	26.47 V	26.77 V	26.96 V	27.16 V	27.37 V
Current (I <sub>mpp</sub> )	6.38 A	6.41 A	6.47 A	6.53A	6.60 A

<sup>&</sup>lt;sup>1</sup> Dimensional tolerance: ±3 mm

This data sheet complies with the specifications of DIN EN 50380.

Available at:

For product and purchase inquries contact:



 $<sup>^2</sup>$  Nominal operating temperature of the cell at 800 W/m² irradiation, 20  $^{\circ}$  C ambient temperature, wind speed of 1 m/s

<sup>&</sup>lt;sup>3</sup> In accordance with IEC 61215 Ed. 2

Weight tolerance: ±0.5 kg/1.1 lbs

<sup>&</sup>lt;sup>5</sup> According to Conergy AG's current warranty conditions

<sup>&</sup>lt;sup>6</sup> Standard Test Conditions defined as follows: 1,000 W/m² radiant power

at a spectral density of AM 1.5 and a cell temperature of 25°C

<sup>&</sup>lt;sup>7</sup> Typical production values